

SINCE 1925

# KEYSTONE

SAFETY ↔ CLEANROOM PRODUCTS

## 1422A TYVEK® CONTINUOUS FORM TUBING



### TYPICAL APPLICATION & CHARACTERISTICS:

Recommended for Steam Sterilization of Pharmaceutical Production Equipment

- Cut to desired length – size flexibility
- Cost Effective
- Tyvek® on both sides for maximum steam penetration during sterilization
- Minimizes the use of autoclave tape
- Fast and consistent for equipment preparation area
- Creates strong seals when heat sealed
- Hydrophobic
- Resists tearing and punctures
- Superior microbial barrier
- Lint-Free
- Manufactured and packaged in ISO certified cleanrooms
- Certificates of Conformance sent with all shipments
- Made in USA

SINCE 1925

# KEYSTONE

SAFETY ↔ CLEANROOM PRODUCTS

# 1422A TYVEK® CONTINUOUS FORM TUBING



## MATERIAL SPECIFICATIONS:

PROPERTY	UNITS	TEST METHOD	TYPICAL VALUES 1422A TYVEK®
Seal Strength	N/mm	F-88	>.78
Basis Weight	g/m <sup>2</sup>	EN ISO 536	41
Total Thickness	μ	EN 20534	130
Air Permeability	s	ISO 5636-5	20
Water Vapor Permeability	G/M <sup>2</sup> /24 HR	ASTM 398	1700
Hydrostatic Head	cm h <sub>2</sub> o	ISO 811	120
Trapezoidal Tear MD/CD	N	ISO 9073-4	26.1/30.6
Linting Propensity	Rating	BS 6909 (Shirley Method 21)	Pass Rating: Excellent
Burst Resistance	kPa	ISO 2960 (50 cm <sup>2</sup> )	108
Puncture Resistance	N	EN 863	10.8
Melting Point	c°		135

KEYSTONE PART NUMBER	DIMENSIONS (cm)
TUBT2A02	5.08
TUBT2A03	7.62
TUBT2A04	10.16
TUBT2A05	12.7
TUBT2A06	15.24
TUBT2A08	20.32
TUBT2A10	25.4
TUBT2A12	30.48
TUBT2A15	38.1
TUBT2A16	40.64
TUBT2A24	60.96
TUBT2A28	71.12
TUBT2A30	76.2
TUBT2A40	101.6

